

PT. ALKINDO MITRARAYA HIGH POLYMER

TECHNICAL DATA

ACRYLINDO 1318-43 AF

I. DESCRIPTION

ACRYLINDO 1318-43 AF is a polyol acrylic resin with good yellowing resistance.

II. PROPERTIES

- Good yellowing resistance
- Good chemical resistance
- Good stain resistance
- Fast tack free

- Color retention
- Hardness
- Adhesion

III. SUGGESTED USES

• PU Wood coating for aromatic free

IV. TYPICAL PROPERTIES

• Resin type : polyol

• Solvent : n-Butyl acetate

arcosolve PMA

V. SPECIFICATION

NV (%) : 43 ± 1
 Viscosity (G-H, 25°C) : Z₁ - Z₃
 AV (mg KOH/g) : max. 7
 Color (Gardner) : max. 1

Appearance : clean and clear

• OHV : 102,75

VI. DILUTABILITY

Aliphatic hydrocarbon
Aromatic hydrocarbon
Ester
Ketone
Alcohol
not dilutable
dilutable
dilutable
dilutable
dilutable
dilutable

VII. PACKING

Resin is supplied in steel drum with net content 200 kgs.

VIII. STORAGE

Store in proper warehouse.

Keep container closed when not in use.

The information contained herein is correct to the best of our knowledge. The recommendations or suggestions contained in this bulletin are made without guarantee or representation as to results. We suggest that you evaluate these recommendations and suggestions in your own laboratory prior to us. Our responsibility for claims arising from breach of warranty, negligence or otherwise is limited to the purchase price of the material.

Jl. Gatot Subroto Km. 8, Desa Kadu Jaya, Kecamatan Curug, Kabupaten Tangerang, INDONESIA - 15810

Phone: +62-21-59302250, Fax: +62-21-59302251