

# PT. ALKINDO MITRARAYA HIGH POLYMER

TECHNICAL DATA

# **ALKINDO 3812-60AF**

#### I. DESCRIPTION

ALKINDO 3812-60AF is an aromatic free of ALK 3812-50.

#### II. PROPERTIES

Fast curing

Hardness

• Good color retention

Good adhesion

Excellent film built

#### III. SUGGESTED USES

Polyurethane for wood finishes.

#### IV. COMPOSITION

: soybean fatty acid • Fatty acid type

Oil length : 33% PA content : 44% OHN (solid) : 165

Solvent : n-butyl acetate (aromatic-free)

## V. SPECIFICATION

NV (%)  $: 60 \pm 1$ Viscosity (G-H, 25°C)  $: X - Z_1$ AV (mg KOH/g) : max. 10 Color (Gardner) : max. 2

: clean and clear Appearance

#### VI. DILUTABILITY

Aliphatic hydrocarbon : not dilutable Aromatic hydrocarbon : dilutable : dilutable Ester Ketone : dilutable Alcohol : dilutable

### VII. PACKING

Resin is supplied in steel drum with net content 200 kgs.

#### VIII. STORAGE

Store in proper warehouse.

Keep container closed when not in use.

The information contained herein is correct to the best of our knowledge. The recommendations or suggestions contained in this bulletin are made without guarantee or representation as to results. We suggest that you evaluate these recommendations and suggestions in your own laboratory prior to us. Our responsibility for claims arising from breach of warranty, negligence or otherwise is limited to the purchase price of the material.

Jl. Gatot Subroto Km. 8, Desa Kadu Jaya, Kecamatan Curug, Kabupaten Tangerang, INDONESIA - 15810

Phone: +62-21-59302250, Fax: +62-21-59302251