

PT. ALKINDO MITRARAYA HIGH POLYMER

TECHNICAL DATA

AMINDO 8738-68

I. DESCRIPTION

AMINDO 8738-68 is a high solid MF resin which has broad compatibility with a wide range of polymers, suitable for automotive & general purpose high solid finishes.

II. PROPERTIES

- Good compatibility with a wide range of polymers
- Excellent hardness and flexibility

III. SUGGESTED USES

• Automotive top coat & general purpose stoving paint.

IV. TYPICAL PROPERTIES

• Resin type : Melamine formaldehyde resin

Alkylation : n-butylatedSolvent : n-butanol

V. SPECIFICATION

NV (%, 150°C - 15 min) : 68.5 - 71
 Viscosity (G-H, 25°C) : W - Y
 AV solution (mg KOH/g) : max. 0.6
 D-30 Tolerance (mL/g) : min. 2.0
 Color (Gardner) : max. 1

Appearance : clean and clear

VI. DILUTABILITY

Aliphatic hydrocarbon : partially dilutable

Aromatic hydrocarbon : dilutable
Ester : dilutable
Ketone : dilutable
Alcohol : dilutable

VII. PACKING

Resin is supplied in steel drum with net content 200 kgs.

VIII. STORAGE

Store in proper warehouse.

Keep container closed when not in use.

The information contained herein is correct to the best of our knowledge. The recommendations or suggestions contained in this bulletin are made without guarantee or representation as to results. We suggest that you evaluate these recommendations and suggestions in your own laboratory prior to us. Our responsibility for claims arising from breach of warranty, negligence or otherwise is limited to the purchase price of the material.

Jl. Gatot Subroto Km. 8, Desa Kadu Jaya, Kecamatan Curug, Kabupaten Tangerang, INDONESIA - 15810

Phone: +62-21-59302250, Fax: +62-21-59302251