

# PT. ALKINDO MITRARAYA HIGH POLYMER

TECHNICAL DATA

# **AMINDO 8788-70**

## I. DESCRIPTION

AMINDO 8788-70 is a high reactivity resin with good compatibility with alkyd and acrylic resins, suitable for high quality baking enamel and can coating.

## II. PROPERTIES

- Good compatibility with alkyd and acrylic resins
- High reactivity

### III. SUGGESTED USES

- High quality baking enamel
- Can coating

#### IV. TYPICAL PROPERTIES

• Resin type : Melamine formaldehyde resin

Alkylation : n-butylatedSolvent : n-butanol

#### V. SPECIFICATION

NV (%, 120°C - 2 hours) : 70 ± 2
 Viscosity (G-H, 25°C) : Z<sub>2</sub> - Z<sub>4</sub>

Viscosity (cps, 25°C) : 2900 – 5800
 AV solution (mg KOH/g) : max. 0.5
 ASTM Tolerance (mL/g) : min. 4.1

Appearance : clean and clear

• FF Content (%) : max. 1.7

#### VI. DILUTABILITY

Aliphatic hydrocarbon : partially dilutable

Aromatic hydrocarbon : dilutable
Ester : dilutable
Ketone : dilutable
Alcohol : dilutable

#### VII. PACKING

Resin is supplied in steel drum with net content 200 kgs.

#### VIII. STORAGE

Store in proper warehouse.

Keep container closed when not in use.

The information contained herein is correct to the best of our knowledge. The recommendations or suggestions contained in this bulletin are made without guarantee or representation as to results. We suggest that you evaluate these recommendations and suggestions in your own laboratory prior to us. Our responsibility for claims arising from breach of warranty, negligence or otherwise is limited to the purchase price of the material.

Jl. Gatot Subroto Km. 8, Desa Kadu Jaya, Kecamatan Curug, Kabupaten Tangerang, INDONESIA - 15810

Phone: +62-21-59302250, Fax: +62-21-59302251