

PT. ALKINDO MITRARAYA HIGH POLYMER

TECHNICAL DATA

AMINDO 9706 - 65

I. DESCRIPTION

AMINDO 9706-65 is a reactive butylated urea melamine formaldehyde resin with good gloss, good hardness, and low odor, designed for extremely low odor acid-curing wood finishes.

II. PROPERTIES

• Good gloss

• Good hardness

• Low odor

Fast curing

• Low ff post cured

• Good stability

III. SUGGESTED USES

Acid curing wood finishes

IV. TYPICAL PROPERTIES

• Resin type : Urea melamine formaldehyde resin

Alkylation : ButylatedSolvent : Xylene

V. SPECIFICATION

NV (%, 120°C - 2 hours) : 65 ± 2
 Viscosity (G-H, 25°C) : Z₄ - Z₆

• Viscosity (cps, 25°C) : 6300 – 14800

AV solution (mg KOH/g) : max. 4ASTM Tolerance (mL/g) : min. 1.5

Appearance : clean and clear

• FF content (%) : max 0.2

VI. DILUTABILITY

Aliphatic hydrocarbon : partially dilutable

Aromatic hydrocarbon : dilutable
Ester : dilutable
Ketone : dilutable
Alcohol : dilutable

VII. PACKING

Resin is supplied in steel drum with net content 200 kgs.

VIII. STORAGE

Store in proper warehouse.

Keep container closed when not in use.

The information contained herein is correct to the best of our knowledge. The recommendations or suggestions contained in this bulletin are made without guarantee or representation as to results. We suggest that you evaluate these recommendations and suggestions in your own laboratory prior to us. Our responsibility for claims arising from breach of warranty, negligence or otherwise is limited to the purchase price of the material.

Jl. Gatot Subroto Km. 8, Desa Kadu Jaya, Kecamatan Curug, Kabupaten Tangerang, INDONESIA - 15810

Phone: +62-21-59302250, Fax: +62-21-59302251